



# Latex Exam Gloves Powder Free, Standard Cuff

Just like this pioneer, GloveOn® Ridley has also conquered many different market segments. It continues to be the most popular choice of powder free latex glove in our range, offering unquantifiable aqueous latex proteins reading, and non-sensitising and non-irritant properties.

NON STERILE	
	GloveOn® Ridley
Length (mm)	
	≥ 230

**Thickness Measurements (mm)** 

Palm (centre of Palm)  $0.13 \pm 0.03$ 

Finger (13mm  $\pm$  3mm from tip) 0.14  $\pm$  0.03

Physical Properties	Before Ageing	After Ageing
Tensile Strength (MPa)	≥ 18	≥ 16
Elongation (%)	≥ 650	≥ 500

Inspection Levels & AQL	Inspection Level	AQL
Watertightness	G1	1.5
Physical Dimensions	\$2	4.0
Tensile Strength	S2	4.0
Visual Inspection (Major)	\$4	2.5
Visual Inspection (Minor)	S4	4.0
Particulate Residue	N = 5	≤ 2mg/glove
Protein Content	N = 3	≤ 50µg/g

<sup>\*</sup>Full test reports on Sensitisation Testing, Primary Skin Irritation and Residual Proteins Testing are available upon request.

### REORDER CODE

CHL11XS X-SMALL
CHL11SS SMALL
CHL11MM MEDIUM
CHL11LL LARGE
CHL11XL X-LARGE

## **FEATURES**

- Fully textured
- Powder free
- Made with natural rubber latex
- Protein level  $\leq 50 \mu g/g$
- Ambidextrous
- Standard cuff
- Natural colour

#### **PACKAGING**

100 gloves per box for XS to XL 10 boxes per carton

# REGULATORY COMPLIANCE

TGA - ARTG 127794, FDA 510(k), REACH, No 1935/2004, EC 1935/2004, CMDR SOR-98-282

## **STANDARDS**

AS/NZS 4011.1:2014, ASTM D3578, CEN/TS 14234, EN 455 part 1, 2, 3 & 4, EN 1186, EN 13130, HACCP Certified, ISO 11193 - 1

MANUFACTURING ACCREDITATIONS ISO 9001:2015

ISO 13485:2003 EN ISO 13485:2012

A brand by



Mun Australia

Toll free: 1800 456 837 (GLOVES) info.au@munglobal.com



